

## Technical Data Sheet

# PERMAPRINT 2013 PLUS

### PERMACOLOR

The PERMACOLOR system is a series of pressure-sensitive products used for mounting and protecting in the photographic and graphic industries. Pressure-sensitive PERMACOLOR provides fast, efficient processing through roll lamination techniques without the need for heat or drying.

### PRODUCT DESCRIPTION

#### **PERMAPRINT 2013 PLUS**

- consists of a thin polyester film coated on both sides with a rubber-based adhesive.
- has medium tack, medium adhesion and high cohesion.
- is produced in a self wound form on a **white moisture stable liner**.
- does not influence the pH level of substrate to which it is applied.

### PHYSICAL PROPERTIES

	<u>Typical values</u>		<u>Test method</u>
	<u>End user</u>	<u>Converter</u>	
<b><u>Adhesive</u></b>			
Quick Tack on glass (N/25 mm)	16	12	FTM 9
Peel 180° on glass (N/25 mm)	14	12.5	FTM 1 (ASTM D 903-49)
- after 20 minutes	14	12.5	FTM 1 (ASTM D 903-49)
- after 24 hours	100	100	FTM 8
Shear on glass (hours) 1 kg - 25 mm x 25 mm			
<b><u>Carrier data</u></b>			
Thickness (μ)	12		ISO 534 (ASTM D 645)
Tensile strength (N/15 mm)	MD ≥ 25 CD ≥ 27		DIN 53455
Elongation (%)	MD ≥ 60 CD ≥ 60		DIN 53455
Tear strength (gr)	MD ≥ 8 CD ≥ 8		
<b><u>Release liner</u></b>			
White moisture stable paper (gr/sqm)	90		ISO 536
<b><u>Thickness</u></b>			
Carrier + adhesive (μ)	60		ISO 534 (ASTM D 645)

## **HEAT RESISTANCE**

Application temperature range : + 10°C to + 40°C  
End-use temperature range : - 30°C to + 90°C

For temperatures outside those quoted above, please consult with MACtac.

## **CHEMICAL RESISTANCE**

Resistant to water, detergents, alcohol and some aliphatic solvents.  
Not recommended for use in contact with ketones, esters, aromatic and chlorinated hydrocarbons.

*For further technical advice, please consult with MACtac.*

## **SHELF LIFE**

2 years when stored at 15 to 25°C and ± 50 % relative humidity.

## **DURABILITY**

**NB** : The durability does not relate to image mounted but only to the mounting film.

For **indoor** applications i.e applications not submitted to strong UV exposure and high temperature, **PP 2013 PLUS** will give satisfactory performance up to 5 years.

For **outdoor** applications, this durability can be reduced to 2 years.

**Note** : *These end-use life estimates are based on accelerated ageing studies and outdoor exposure, under conditions experienced in vertical exposure and in "normal" temperate climates. Exposure to severe humidity and ultraviolet light, as in southern European countries, and also in tropical, sub-tropical or desert regions, will cause a more rapid deterioration. This also applies to polluted areas, high altitude and south-facing exposure.*

## **RECOMMENDATIONS**

- When using **PP 2013 PLUS** onto polycarbonate, polystyrene, polymethyl-methacrylate substrates, it is recommended to conduct compatibility tests in normal use conditions. These types of panels tend to « degas » when exposed to temperature, creating bubbles and/or tunnels between the panels and the mounting film. Conditioning these panels overnight in a room above 60°C before mounting helps prevent damage occurring.
- It is recommended to condition the paper image (more humid than dry) before mounting it to a board. This will avoid moisture reabsorption, which may cause the mounted paper image to swell and then cause a tunnelling effect between the mounting film and the paper image.

### **IMPORTANT NOTICE**

*All MACtac products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects.  
Published information concerning MACtac products is based upon research which the Company believes to be reliable although such information does not constitute a warranty.  
Because of the variety of uses of MACtac products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. The seller shall not be liable for damages in excess of the purchase price of the product nor for incidental or consequential damages.  
All specifications are subject to change without prior notice.*