



Self-adhesive Digital Imaging Media for wide-format inkjet Printing

JT 5425 PUV

Technical Data Sheet

2 year Top Coated modified PO film

PRODUCT DESCRIPTION

FACE MATERIAL : 100 μ White gloss top coated modified PO film
 ADHESIVE : Permanent clear emulsion acrylic.
 LINER : Coated Kraft liner 120 gsm

TYPICAL USES

White Gloss, **non PVC film**, for short to medium term, indoor or outdoor advertising or promotion on flat or slightly curved surfaces.

This film is 100% Chlorine & Phthalate free!

PRINTING

Especially designed for wide-format UV inkjet printing using flexible UV inks.

To achieve the best possible print quality, please make sure that the correct ICC profiles or printer settings are used. Profiles can be obtained from our Subsidiaries, Distributors or can be downloaded from www.mactac-europe.com. Printer & Heater settings and ICC profiles are also downloadable from some of the OEM's web sites.

PHYSICAL PROPERTIES OF THE UNPRINTED FILM

	Average values	Test method
Adhesive Data, 23°C		
Quick Tack on glass	12 \pm 3.0 N/25 mm	FTM 9
Peel 24 hours on glass	13 \pm 2 N/25 mm	FTM 1
Dimensional stability		
shrinkage : 48 hours at 70°C (applied on aluminium)	max 0.2 mm	FTM 14
Temperature ranges		
Minimum application temperature :	+10°C	
Service temperature range :	- 20C to + 70°C	

SHELF LIFE

2 years when stored at 15 to 25°C and \pm 50 % relative humidity (in the original packaging).

DURABILITY

The outdoor durability of the unprinted film is 2 years.

RECOMMENDATIONS

Always test the combination of JT 5000 products, inks and laminating films prior to commercial use.

Printing conditions

A conditioned pressroom, $\pm 23^{\circ}\text{C}$ and 50 % R.H.

Laminating

If the printed graphics is likely to be exposed to corrosive liquids, smoke, fumes, highly polluted areas or if there is a likelihood of scratching or friction or to ensure longer durability, **it is strongly recommended to laminate the prints with pressure-sensitive protective films Permacolor LUV 7036 (PET film) or LUV 3800 series (PVC film).**

MACtac denies responsibility for product failure if non-MACtac laminting films are used for the application.

Transportation conditions

To allow easy transportation, IMAGin JT series can be rolled up, with the image on the outside, with a minimum diameter of 15 cm (for example on a 6 inches core). To avoid exposing the print to any liquid aggressions, prints should be protected by a plastic bag. During the transport or storage of the prints, avoid exposing them to extreme temperature and humidity variations.

GENERAL REMARK : factors affecting adhesion

To ensure application suitability - always test the proposed construction under actual application and end-use conditions before going into full production.

The following factors will adversely affect adhesion of a pressure-sensitive adhesive:

- * Dusty, dirty, oily or oxidized surfaces
- * Mould release agents on blow-moulded plastic surfaces
- * Low surface energy substrates, such as: polyethylene, polypropylene...
- * Application below the minimum application temperature or use outside of the recommended service temperature ranges.

IMPORTANT NOTICE

All MACtac products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects.

Published information concerning MACtac products is based upon research which the Company believes to be reliable although such information does not constitute a warranty.

Because of the variety of uses of MACtac products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. The seller shall not be liable for damages in excess of the purchase price of the product nor for incidental or consequential damages.

All specifications are subject to change without prior notice.