

LAMINATED FOIL MP 710N

Century 8 WH

FACE MATERIAL

Laminated Foil is a very thin aluminium foil laminated on a wood free paper.

The surface is metallized and vinyl lacquered for better printing.

For applications on very curved surfaces (< 25mm diameter), we recommend our Macflex face stock.

Application

Laminated Foils are designed for the production of high quality and prestige labels over a wide range of end-uses such as luxury foods, cosmetics, sports goods, etc. Available in four appealing finishes, bright gold and silver as well as dull gold and silver.

Technical Characteristics

Thickness	60 ± 5 µ	ISO 534
Weight	82 ± 5 gr/sqm	ISO 536
Tensile strength	min. 52 N/15 mm M.D. min. 26 N/15 mm C.D.	ISO 1924-2

ADHESIVE

Permanent rubber based adhesive developed to answer both printers' productivity and end users requirements . It offers high initial tack and very good adhesion on a wide range of surfaces.

This hot melt adhesive performs well on difficult substrates.

Certification : Direct contact dry and moist non-fatty foodstuffs (29948 U 10)

Properties

Quick Tack	≥ 16	N/25 mm on glass	FTM 9
Application temperature	above -5 °C	<i>*Under 0°C, the application guaranty is mainly depending on the kind of face and substrate used. Prior test is recommended</i>	
Service temperature	- 30 °C to + 60 °C		

BACKING

Super calendered glassine backing paper combining high flexibility and consistent calliper for speed and ease of conversion with good translucency for optical scanning. Excellent resistance to die-cutting.

Technical Characteristics

Thickness	68 ± 6 µm	ISO 534
Weight	80 ± 4 gr/m ²	ISO 536
Tensile strength MD	≥ 90 N/15 mm	DIN 53455
Transparency	≥ 42 %	DIN 53147

Shelf life: 2 years when stored at 15-25°C, (50 ± 5) % relative humidity, in the original packaging.



MACtac Europe
Bd Kennedy, Zoning Industriel, Zone B
B-7060 Soignies Belgium
Phone : +32 (0) 67 346 211
Fax : +32 (0) 67 346 339
www.mactac-europe.com
e-mail : mactac.europe@mactac.com



All MACtac products are subject to careful quality control throughout the manufacturing process and are warranted to be of quality and free from manufacturing defects.

Published information concerning MACtac products is based upon research which the Company believes to be reliable although such information does not constitute a warranty.

Because of the variety of uses of MACtac products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. The seller shall not be liable for damages in excess of the purchase price of the product nor for incidental or consequential damages. All specifications are subject to change without prior notice.