

# **MACal® 8200 PRO**

## *Technical Data Sheet*

### **PRODUCT DESCRIPTION**

MACal 8200 Pro is a calendered soft vinyl films coated with a permanent acrylic adhesive.  
MACal 8200 Pro have been specially developed for trouble-free computer cutting and fast weeding, even for small letters and fine lines.

### **CONSTRUCTION**

#### **Face material :**

Calendered vinyl film, 75 µm thick, cadmium-free.

#### **Adhesive :**

High quality water based permanent acrylic adhesive.

#### **Liner :**

Highly stable 130 gsm white kraft paper with grey backprinting.

For white vinyls, the liner is coated with a grey silicone coating to improve the contrast with the film colour.

NB : **CONTRAST** ensures a clear view during the stripping process therefore improving productivity.

### **TYPICAL USES**

MACal 8200 PRO is a medium term marking film designed for indoor applications (exhibition stands) and for outdoor applications (vehicle marking, window graphics, signs...).

### **EXPECTED DURABILITY**

The expected vertical outdoor durability of the unprocessed product in central Europe (Zone 1) is up to:

4 years : black and white.

3 years : all colours.

This information is based on successful real life experience and artificial aging according to ISO4892-3.

**Note :** Exposure to severe temperatures and ultraviolet light, as well as conditions in southern European countries, and also in tropical, sub-tropical or desert regions, will cause a more rapid deterioration. This also applies to polluted areas, high altitude, horizontal and south-facing exposure.

### **SHELF LIFE**

2 years when stored at 15 to 25°C and ± 50 % relative humidity.

### **PHYSICAL PROPERTIES** (Typical values)

**Thickness** (mm) (Film + adhesive) ISO 534  
0.095

**Face Material Data, 23°C** DIN 53455-5

Tensile strength : > 25 N/15mm

Elongation at break : ≥ 150 %

#### **Adhesive Data, 23°C**

FTM 1

Peel adhesion 180° on stainless steel (N/25mm)

- 20 min. residence : 12

- 24 hours residence : 16

- 1 week residence : 18

#### **Dimensional stability**

FTM 14

Shrinkage (48 hours at 70°C) : < 0.2 %

(25 cm x 25 cm, sample mounted on aluminium).

#### **Temperature ranges :**

Application : + 8°C to + 40°C

End-use : - 40°C to + 80°C

N.B. : for lower temperatures, please consult us.

#### **Flammability**

ISO 3795

Sample mounted on aluminium : self-extinguishing.

#### **Solvent and chemical resistance**

Water, water and detergent, alcohols : unaffected.

Oil, gasoline, gasoline-oil : affected (lifting around edges).

### **PROCESSING**

#### **Computer cutting**

Clean, quick, trouble-free cutting with most plotters.

Adjustment of the cutting depth is important : if the cut is too deep this could result in the paper splitting and coming away with the adhesive when the vinyl is transferred to Application Tape.

#### **Weeding**

Easy and fast weeding even for small letters and fine lines.

#### **Application**

The transfer of the cut vinyl onto the Application Tape should always be performed by removing the liner from the pressure-sensitive material (i.e. with the PVC face downwards onto the working surface) and not by lifting off the Application Tape.

MACal 8200 PRO can be applied with the dry or wet application method on flat surfaces.

#### **Important remark**

All surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination.

The compatibility of paints and lacquers should be tested by the end-user, prior to use.

#### **Edge sealing and varnishing**

Where exposure to chemicals and solvent spillage is likely to occur, edge sealing of decals with a varnish will prevent edge lift. Correct varnishing of decals gives greater protection, and extends the use-life against prolonged effects of weathering, abrasion and other effects such as frequent cleanings.

**IMPORTANT NOTICE**

*All MACTac products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects.*

*Published information concerning MACTac products is based upon research which the Company believes to be reliable although such information does not constitute a warranty.*

*Because of the variety of uses of MACTac products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. The seller shall not be liable for damages in excess of the purchase price of the product nor for incidental or consequential damages.*

*All specifications are subject to change without prior notice.*