

MACCoat WS MP 710 N Century 8 WH

FACE MATERIAL

White wood free one side coated wet strength paper .

MACCoat WS is printable by all common print processes such as rotogravure, offset and hot foil stamping.

Application

It is used for any high quality multi-colour printing. MaCcoat WS is specially suited for labelling in humid environments.

Technical Characteristics

Weight	70 ± 5 gr/sqm	ISO 536
Gloss	max 90 %	DIN 67530
Opacity	min 84 %	ISO 2471

ADHESIVE

**Permanent rubber based adhesive developed to answer both printers' productivity and end users requirements . It offers high initial tack and very good adhesion on a wide range of surfaces.
This hot melt adhesive performs well on difficult substrates.**

Certification : Direct contact dry and moist non-fatty foodstuffs (29948 U 10)

Properties

Quick Tack	≥ 15	N/25 mm on glass	FTM 9
High release force	0,17 ± 0,06	N/25 mm at 100 m/min.	FTM 4
Application temperature	above -5 °C	<i>Under 0°C, the application guaranty is mainly depending on the kind of face and substrate used. Prior test is recommended.</i>	
Service temperature	- 30 °C to + 60 °C		

NB : adhesion data based on limited number of production runs

BACKING

Super calendered glassine backing paper combining high flexibility and consistent caliper for speed and ease of conversion with good translucency for optical scanning.Excellent resistance to die cutting.

Technical Characteristics

Thickness	68 ± 6 µm	ISO 534
Weight	80 ± 5 gr/m ²	ISO 536
Tensile strength	min. 100 N/15 mm	M.D. ISO 1924-2
Transparency	minimum 43 %	DIN 53147

Shelf life: 2 years when stored at 15-25°C, (50 ± 5) % relative humidity, in the original packaging.



MACtac Europe
Bd Kennedy, Zoning Industriel, Zone B
B-7060 Soignies Belgium
Phone : +32 (0) 67 346 211
Fax : +32 (0) 67 346 339
www.mactac-europe.com
e-mail : mactac.europe@mactac.com



All MACtac products are subject to careful quality control throughout the manufacturing process and are warranted to be of quality and free from manufacturing defects.

Published information concerning MACtac products is based upon research which the Company believes to be reliable although such information does not constitute a warranty.

Because of the variety of uses of MACtac products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. The seller shall not be liable for damages in excess of the purchase price of the product nor for incidental or consequential damages. All specifications are subject to change without prior notice.