

Supergloss MP125S Secury 9

FACE MATERIAL

White wood free cast coated paper with mirror finish, elemental chlorine free paper.

Supergloss is printable by all common print processes such as flexo, letterpress, screen and hot foil stamping.

Application

It is used for any high quality multi-colour printing when the highest gloss level is required, like for prestige articles etc.

Technical Characteristics

Thickness	80 ± 3 µm	ISO 534
Weight	88 ± 5 gr/sqm	ISO 536
Tensile strength	min. 4 kN/m	M.D. ISO 1924-2
Opacity	≥ 89 %	ISO 2471

ADHESIVE

Permanent acrylic adhesive, emulsion based, offering a perfect combination of quick tack and shear resistance, and outstanding adhesion to most substrates. This adhesive is a multi-purpose one suitable for high converting speeds.

Certification : upon request

Properties

Quick Tack	min 10	N/25 mm on glass	FTM9
Low release force	0,07 ± 0,02	N/25 mm at 300 mm/min	FTM3
Application temperature	Above + 5°C	<i>The product can be used outside the indicated service temperature range for a short period of time (e.g : the heat developed in a laser printer can reach 180°C).</i>	
Service temperature	- 15°C to + 80°C		

BACKING

Special quality white one side coated siliconed kraft backing paper.

Excellent mechanical properties such as dimensional stability. Very good characteristics for fan folding applications.

Technical Characteristics

Thickness	90 ± 7 µm	ISO 534
Weight	80 ± 6 gr/m ²	ISO 536
Opacity	minimum 85 %	ISO 2471

Shelf life: 2 years when stored at 15-25°C, (50 ± 5) % relative humidity, in the original packaging.



MACTac Europe
Bd Kennedy, Zoning Industriel, Zone B
B-7060 Soignies Belgium
Phone : +32 (0) 67 346 211
Fax : +32 (0) 67 346 339
www.mactac-europe.com
e-mail : mactac.europe@mactac.com



All MACTac products are subject to careful quality control throughout the manufacturing process and are warranted to be of quality and free from manufacturing defects.

Published information concerning MACTac products is based upon research which the Company believes to be reliable although such information does not constitute a warranty.

Because of the variety of uses of MACTac products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. The seller shall not be liable for damages in excess of the purchase price of the product nor for incidental or consequential damages. All specifications are subject to change without prior notice.