

SUPEROPAQUE MP 710N-2 Century 6

FACE MATERIAL

White wood free, coated paper with satin aspect , laminated with an aluminium foil which provides a complete opacity.

The paper face is printable by all common processes such as letterpress, flexo, gravure and offset.

Application

Superopaque is specially used when total opacity is required : for masking old prices, printing errors, text errors, out-of-date information or for texts to be over-printed or modified.

Technical Characteristics

Thickness	60 ± 5 µ	ISO 534
Weight	82 ± 5 gr/sqm	ISO 536
Tensile strength	min. 52 N/15 mm M.D. min. 26 N/15 mm C.D.	ISO 1924-2

ADHESIVE

Permanent rubber based adhesive with increased coating weight combining all purpose properties with very high initial tack. This Hot Melt is suitable for use on a wide variety of very difficult substrates

Certification : Indirect contact foodstuffs (29948 U 10)

Properties*

Quick Tack	min. 22	N/25 mm on glass	FTM 9
Release force	0.20 ± 0.05	N/25 mm - 100 m/min	FTM 4
Application temperature	+0°C		
Service temperature	-30°C to +60°C		

**Based on a limited production sample*

BACKING

Super calendered glassine backing paper combining high flexibility and consistent caliper for speed and ease of conversion with good translucency for optical scanning. Excellent resistance to die cutting.

Technical Characteristics

Thickness	55 ± 6 µm	ISO 534
Weight	60 ± 5 gr/m ²	ISO 536
Tensile strength	Minimum 75 N/15mm M.D.	ISO 1924-2
Transparency	minimum 46 %	DIN 53147

Shelf life: 2 years when stored at 15-25°C, (50 ± 5) % relative humidity, in the original packaging.



A Bemis Company

MACTac Europe
Bd Kennedy, Zoning Industriel, Zone B
B-7060 Soignies Belgium
Phone : +32 (0) 67 346 211
Fax : +32 (0) 67 346 339
www.mactac-europe.com
e-mail : mactac.europe@mactac.com



All MACTac products are subject to careful quality control throughout the manufacturing process and are warranted to be of quality and free from manufacturing defects.

Published information concerning MACTac products is based upon research which the Company believes to be reliable although such information does not constitute a warranty.

Because of the variety of uses of MACTac products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. The seller shall not be liable for damages in excess of the purchase price of the product nor for incidental or consequential damages. All specifications are subject to change without prior notice.